

WATEX CEILING

Spray Application	<u>Airless Spray</u>
	Delivery Pressure (kg/cm ²) 120 - 150
	Tip size at 60° angle 0.017"
	Dilution 10% maximum
Recommended Painting System	- 1 - 2 coats NIPPON SKIMCOAT - 1 coat MATEX SEALER - 2 coats WATEX CEILING
Recommended Film Thickness per coat	30 - 40 microns DFT (Dry Film Thickness) per coat for standard application
Drying Time	Surface dry - 10 minutes at 30 °C
Overcoating Time	2 hours. Minimum based on normal conditions.
Cleaning	Wash all equipment immediately after use with clean water
Storage	Keep containers tightly closed. Store in a cool, dry and well-ventilated place at temperature between 5 to 40 °C.
Packing	5 Liters & 18 Liters Containers
Precaution	Coverage depends on film thickness, roughness or porosity of the surface, loss during painting, etc. The actual drying time and time before recoating may be shorter or longer, depending on film thickness, temperature, ambient humidity, ventilation, etc. Avoid painting when the temperature is below 10°C and the humidity is over 85%. Avoid direct contact with sensitive skin. Use appropriate protective equipment.
NOTE	<i>The information given applies to the product and its performance under specific test conditions. Due to the varied circumstances beyond our control under which the product may be applied, for specific application, please contact Nippon Paint Sales & Marketing Dept. We reserve the right to modify our product data sheet without further notice.</i>